

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> C08L 83/04, C08F 283/12 C08G 77/06	<b>A1</b>	<b>(11) International Publication Number:</b> WO 93/08236 <b>(43) International Publication Date:</b> 29 April 1993 (29.04.93)
<b>(21) International Application Number:</b> PCT/US92/09039 <b>(22) International Filing Date:</b> 23 October 1992 (23.10.92)  <b>(30) Priority data:</b> 794,292                      25 October 1991 (25.10.91)      US  <b>(71) Applicant:</b> NUSIL TECHNOLOGY [US/US]; 1040 Cindy Lane, Carpinteria, CA 93013 (US). <b>(72) Inventor:</b> NASH, Brian ; 1326 Vallecito Place, Carpinteria, CA 93013 (US). <b>(74) Agent:</b> PETIT, Michael, G.; 510 Castillo Street, Santa Barbara, CA 93101 (US).		<b>(81) Designated States:</b> AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> COMPOSITION AND METHOD FOR TEXTURING THE SURFACE OF ARTICLES  <b>(57) Abstract</b>  Novel one and-two-part silicone dispersions are described which are suitable for applying a durable textured silicone surface on both silicone and non-silicone articles. The non-blocking surface is obtained by dip-coating a final layer over an article wherein the dispersion used for the final layers comprises a unique hydrophilic silica filler having a specific surface area of about 75-200 m <sup>2</sup> per gram, at least one crosslinkable polysiloxane and a crosslinking agent. The silica particles, securely imbedded within the final layer of silicone with portions thereof extending outwardly beyond the new outer silicone surface of the article, present a non-blocking, non-allergenic textured surface.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SK	Slovak Republic
CI	Côte d'Ivoire	LK	Sri Lanka	SN	Senegal
CM	Cameroon	LU	Luxembourg	SU	Soviet Union
CS	Czechoslovakia	MC	Monaco	TD	Chad
CZ	Czech Republic	MG	Madagascar	TG	Togo
DE	Germany	ML	Mali	UA	Ukraine
DK	Denmark	MN	Mongolia	US	United States of America
ES	Spain			VN	Viet Nam
FI	Finland				

COMPOSITION AND METHOD FOR TEXTURING  
THE SURFACE OF ARTICLES

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to a composition and method for making a silicone article that has a textured non-blocking surface.

2. Prior Art

As is well known in the art, silicone articles may be formed by dipping or otherwise depositing a dispersion of silicone on an appropriate form. The dispersion may also contain a vulcanizing agent along with accelerators and other additives. After each layer of dispersion is deposited on the form, the layer is permitted to cure and the process is repeated until the outer shell of the article reaches the required thickness.

A smooth untreated elastomer surface has the physical characteristic of blocking; that is, the characteristic of sticking to itself and other surfaces. For some applications blocking is undesirable. For example, blocking is undesirable in latex, silicone and other elastomer gloves because it makes them difficult to don. Various lubricants and release agents have been dusted or otherwise applied to gloves to improve performance and overcome blocking. The shedding of these lubricants can cause undesirable side-effects, such as contamination, infection and foreign body reactions due to powders from gloves entering the wound during surgical procedures. As a result, much of the early work on

1 textured surfaces was performed on latex surgical gloves. U.S.  
2 Patent No. 3,761,965, discloses a sanitary glove having a textured  
3 surface provided by a granular vinyl chloride polymer imbedded on  
4 the surface of the film from which the glove is manufactured. This  
5 glove is suitable for donning without the use of a lubricant such  
6 as powder. However, this type of glove has the same type of  
7 problem as talc-dusted gloves in that particulates may enter a  
8 wound causing an adverse foreign body reaction. Dusted gloves are,  
9 therefore, not generally suitable for surgical procedures.

10 U.S. Patent No. 1,983,963 discloses a method of providing  
11 a textured surface on a rubber glove which subjects the vulcanized  
12 surface of the glove to the action of a rubber solvent or swelling  
13 agent such as naphtha, benzol, or gasoline either by immersion of  
14 by subjecting the surfaces to the fumes of these chemicals. This  
15 process, which is similar to etching, has not enjoyed widespread  
16 use and is not adaptable to silicone.

17 U.S. Patent No. 4,143,109, issued to Stockum, describes  
18 a method of dip-coating a first layer of natural rubber latex onto  
19 a glove form, the form having the general contour of a human hand,  
20 followed by dip-coating a second layer containing particulates  
21 which are randomly distributed throughout dispersion. After  
22 curing, the glove is inverted and may be donned without the use of  
23 lubricants. The general method developed by Stockum for latex

1 articles has not been transferrable to silicone articles because  
2 the particulates taught by Stockum for use with latex would weaken  
3 the outermost layers of silicone substantially.

4           The foregoing inventions have been developed for latex  
5 articles. U.S. Patent no. 4,061,709 to Miller, et al., describes  
6 a method for manufacturing silicone rubber gloves with a non-  
7 blocking surface by repeatedly dipping a form in a solvent  
8 dispersion of uncured silicone rubber to build up a plurality of  
9 layers and then forming a layer of liquid droplets on the surface  
10 of the article thereby forming an irregular or textured surface as  
11 the solvent evaporates. Utilization of this method for physically  
12 altering the exterior uniformly from lot to lot requires a highly  
13 controlled manufacturing environment which is difficult and  
14 expensive to maintain. The present invention utilizes a unique  
15 dispersion which produces a uniformly textured, non-blocking  
16 surface.

17           There are other areas where a non-organic, non-  
18 contaminating, non-blocking, non-allergenic, texturized surface  
19 with low reflectivity and high diffusivity would be highly  
20 advantageous. Some space applications demand low reflectivity or  
21 high diffusivity in paints and coatings. Epoxies, and almost all  
22 organic coatings other than silicone, are not durable enough to  
23 withstand the highly oxidizing atmospheres that satellites must

1 endure. For example, an anti-blocking silicone surface is  
2 necessary in a bellows or in rolled solar array to facilitate  
3 separation of adjacent surfaces during deployment. Until now,  
4 prior art silicone technology has not been able to produce  
5 contaminant-free silicone anti-blocking, low reflectivity, high  
6 diffusivity outer layers which are sufficiently durable to  
7 withstand the physical and chemical properties of these extreme  
8 environments.

9 SUMMARY OF THE PRESENT INVENTION

10 The invention general contemplates providing a new and  
11 improved composition and process which enables both silicone and  
12 non-silicone articles to be coated with silicone and textured *in*  
13 *situ*. Texturizing is brought about by the incorporation of  
14 hydrophilic silica in a silicone dispersion used for a final  
15 coating or texturing dip. In the final dispersion of the dipping  
16 process, the silica particles are incorporated within the outermost  
17 layer and stand up away from the surface providing a textured  
18 unblocking surface, while, at the same time, not substantially  
19 weakening the article or permitting delamination of the textured  
20 final layer.

21 It is an object of the invention to provide a composition  
22 for making a silicone article having an integral textured non-  
23 blocking outer surface, which surface is formed *in situ*; and to

1 provide a method for making the same.

2 It is yet another object of this invention to provide a  
3 composition and method useful for applying a textured silicone  
4 coating to both silicone and non-silicone articles.

5 It is yet a further object of the invention to provide a  
6 composition for applying a contaminant-free outer surface to an  
7 article.

8 It is still a further object of the invention to provide  
9 a composition for applying a textured, non-allergenic outer surface  
10 to an article.

#### 11 DESCRIPTION OF PREFERRED EMBODIMENTS

12 This invention teaches the addition of hydrophilic silica  
13 preferably in the size range of 2-10 microns, to elastomer  
14 dispersion to provide a textured non-blocking silicone surface  
15 coating on articles dipped therein. Dipping articles in elastomer  
16 dispersions is well known in the art of applying elastomer  
17 coatings. Suitable silicone dispersions for applying smooth, non-  
18 textured coatings to articles are also well known in the art. What  
19 has been unknown in the art until the invention thereof by the  
20 present inventor is the addition of hydrophilic silica to a  
21 silicone dispersion to render a textured surface to articles coated  
22 therewith.

23 The addition of colloidal silica to elastomer dispersions



1 is also well known in the art. The function of added colloidal  
2 silica is to strengthen the elastomer upon curing. Colloidal  
3 silica, which is hydrophobic (organophilic), is obtained by the  
4 surface treatment of silica with organic moieties to generate a  
5 particulate species capable of colloidal dispersion. While the  
6 addition of colloidal silica to a silicone dispersion strengthens  
7 the resultant elastomer layer, the dispersion is inoperative for  
8 providing a textured surface to an article coated therewith.  
9 Surprisingly, adding hydrophilic silica, preferably in the size  
10 range 2-10 microns, to a dispersion does provide a textured surface  
11 to an article coated therewith. Colloidal silica is too dense for  
12 the particles to "float" to the surface while the layer is curing.  
13 It is important that the silica particles have a large specific  
14 surface area and a density such that the hydrophilic silica  
15 particles "float" in an elastomer dispersion thereby migrating to  
16 the surface of a layer coated with such dispersion.

17 Example 1: FIRST PREFERRED EMBODIMENT

18 The present invention is directed to the task of  
19 improving the surface morphology of articles, including silicone  
20 articles, to provide a textured surface which has a lower  
21 coefficient of friction than a smooth surface and which is suitable  
22 for coating articles such as surgical gloves which presently  
23 require lubricants to enable donning.

1           In accordance with the invention, the surface morphology  
2 of articles is substantially improved by bonding to the surface a  
3 silicone coating comprising the reaction product of a composition  
4 comprising: (1) at least one crosslinkable polysiloxane; (2)  
5 silica filler; (3) crosslinking catalyst; (4) a crosslinking agent.  
6 The coating may be applied to the surface from a liquid vehicle,  
7 preferably a volatile organic solvent, followed by heating to drive  
8 off the organic solvent or other liquid vehicle and to effect  
9 crosslinking. The manner of application, whether by dipping,  
10 flowing, spraying, etc. is a matter of individual choice and per se  
11 comprises no part of this invention.

12           An example of a two-part silicone dispersion which, when  
13 combined and applied to the surface of an article, and allowed to  
14 cure, produces a durable textured, non-blocking surface on said  
15 article, is as follows:

	Part A	Part B
	% by weight	% by weight
16 Trifluoropropyl methyl polysiloxane	0 - 100%	0 - 100%
17 Dimethyl polysiloxane	0 - 100%	9 - 100%
18 Dimethyl diphenyl polysiloxane	0 - 30%	30 - 0%

1	Catalyst	0 - 20 ppm	-0-
2	X linker	-0-	0 - 10%
3	Hydrophilic silica	1 - 20%	1 - 20%
4	Reinforcing silica	0 - 40%	0 - 40%

5  
6           The coating composition of this invention is readily  
7 prepared by mixing the ingredients under ambient temperature and  
8 pressure. The surface may then be coated by per se known  
9 techniques, dipping in the coating solution being more efficacious.

10           Crosslinking, as well as solvent removal, is effected by  
11 heating at a temperature and for a time to effect complete cure as  
12 well as solvent removal. Since there is a time-temperature  
13 relationship to effect cure, the time and temperature are not  
14 susceptible to precise quantitative statements. On a bench scale,  
15 heating at about 150°C for about 30 minutes is effective.

16           Example 2: SECOND PREFERRED EMBODIMENT

17           A second system which is suitable for using as a final  
18 coat dispersion for producing textured surfaces on silicone and  
19 non-silicone articles is a one-part system similar to the two-part  
20 system described in Example 1. The one-part system utilizes, for  
21 example, dimethyl polysiloxane (0-100%), Dimethyl diphenyl  
22 polysiloxane (30-0%), hydrophilic silica having a specific surface

1 area between 75-200 square meters per gram (0-20%), tris  
2 (methylethyl ketoximo) methylsilane (<10%) and a catalyst (organo-  
3 tin complex) in naphtha. Before the above dispersion is suitable  
4 for a final application, the percentage of texturing silica (e.g.  
5 Degussa TS-100) must be adjusted to fall within the range of about  
6 0-20% by solids weight. Solvent for the final dilution runs from  
7 0-70% by solids weight.

## CLAIMS

What I claim is:

1. In a one or two part dispersion of a silicone elastomer in a organic solvent, the improvement comprising the addition of hydrophilic silica to said dispersion to provide a textured surface to an article coated with said dispersion.

2. The improved dispersion of Claim 1 wherein the hydrophilic silica has a particle size of 2-10 micrometers and a specific surface area of 75-200 square meters per gram.

3. The improved dispersion of Claim 1 wherein said silicone elastomer is a copolymer comprising dimethyl polysiloxane.

4. The improved dispersion of Claim 1 wherein said elastomer is a copolymer comprising dimethyl diphenyl polysiloxane.

5. The improved dispersion of Claim 2 wherein said silicone elastomer is a copolymer comprising dimethyl polysiloxane.

6. The improved dispersion of Claim 2 wherein said elastomer is a copolymer comprising dimethyl diphenyl polysiloxane.

7. An article having a textured outer surface made by the process comprising (a) coating the article in a dispersion of silicone elastomer in an organic solvent to which dispersion hydrophilic silica has been added; and (b) curing the coating.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US92/09039

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : C08L 83/04; C08F 283/12; C08G 77/06

US CL : 524/860, 869; 525/474; 528/18

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/860, 869; 525/474; 528/18

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	US, A, 4,569,980 (SASAKI ET AL) 11 FEBRUARY 1986, see entire document.	1-7 2,5,6
A	US, A, 4,950,502 (SAAM ET AL) 21 AUGUST 1990, see entire document.	1-7
A	US, A, 4,560,711 (SUZUKI) 24 DECEMBER 1985, see entire document.	1-7
A	US, A, 4,087,399 (HAMADA ET AL) 02 MAY 1978	1-7

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

22 December 1992

Date of mailing of the international search report

05 JAN 1993

Name and mailing address of the ISA/  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

MARGARET GLASS

Telephone No. (703) 308-2351